

Accura® Xtreme™ White 200

Ultra-tough white plastic with outstanding durablity, accuracy and aesthetics to replace CNC-machined polypropylene and ABS articles.

Tough/Durable Class

Stereolithography (SLA)

GET EXTREME PERFORMANCE AND DURABILITY

With outstanding toughness, Accura Xtreme White 200 offers high elongation at break, high impact strength and the stiffness and durability of Polypropylene and ABS plastics. This material is the top choice for functional assemblies that must stand up to the harshest, most demanding environments and it is even good for drill/tap applications.

The Accura Xtreme White 200 exhibits fast build speeds for high throughput, excellent detail fidelity and nice sidewall quality, reflecting a stunning white finish that replicates the look and feel of an injection molded part.

Liquid Material

MEASUREMENT	CONDITION	VALUE
Viscosity	@ 30 °C (86 °F)	650-750 cps
Penetration Depth (Dp)		4.6 mils
Critical Exposure (Ec)		8.3 mJ/cm ²
Color		White
Liquid Density	@ 25 °C (77 °F)	1.12 g/cm³ 0.04 lbs/in³

Printer Compatibility/Packaging:

ProJet® 6000/7000 SLA printers:

ProX® 800, iPro™ 8000, ProX 950 SLA printers:

Viper si2™, SLA 5000 and SLA 7000 printers:

10 kg cartridge

10 kg standard bottle

APPLICATIONS

- · Form, fit and function prototypes
- Durable and challenging assemblies
 - Snap fit assemblies
 - Assemblies with self-tapping screws
 - Tough enclosures
 - $\hbox{-} \ {\sf Consumer} \ {\sf electronic} \ {\sf components} \\$
- General purpose prototyping
- Master patterns for RTV/silicone molding
- Replace CNC machining of Polypropylene and ABS

BENEFITS


- · Robust parts resisting breakage
- Handles challenging functional assemblies
- Increased application opportunities
- Aesthetics of molded parts
- Ease-of-use and fast processing

FEATURES

- Outstanding durability and impact resistance
- Look and feel of a durable molded plastic
- Excellent accuracy
- · Good moisture resistance
- Low viscosity formulation







Accura® Xtreme™ White 200

Tough/Durable Class

Stereolithography (SLA)

Ultra-tough white plastic with outstanding durablity, accuracy and aesthetics to replace CNC-machined polypropylene and ABS articles.

Post-Cured Material

MECHANICAL PROPERTIES		LARGE FRAME SLA PRINTERS		PROJET SLA PRINTERS ¹			
MEASUREMENT	CONDITION	METRIC	U.S.	METRIC	U.S.		
Tensile Strength (MPa PSI)	ASTM D 638	45-50	6530-7250	48	6960		
Tensile Modulus (MPa KSI)	ASTM D 638	2300-2630	334-381	2630	381		
Elongation at Break	ASTM D 638	7-20 %		14 %			
Flexural Strength (MPa PSI)	ASTM D 790	75-79	10880-11460	74	10730		
Flexural Modulus (MPa KSI)	ASTM D 790	2350-2550	341-370	2390	347		
Impact Strength (J/m Ft-lbs/in)	ASTM D 256	55-66	1.0-1.2	65	1.2		
Heat Deflection Temperature @ 0.45 MPa (66 PSI) @ 1.82 MPa (264 PSI)	ASTM D 648	47 °C 42 °C	117 °F 108 °F	47 °C 42 °C	117 °F 108 °F		
Coefficient of Thermal Expansion (CTE) (μm/m-°C μin/in-°F)	ASTM E 831-93 30-50 °C 70-140 °C	95 180	53 100	NA NA	NA NA		
Glass Transition (Tg)	DMA, E"	52 °C	126 °F	65 °C	149 °F		
Hardness, Shore D		78-80		80			
Water Absorption	ASTM D 570-98	0.38 %		NA			
Solid Density (g/cm³ lbs/in³)	@ 25 °C (77 °F)	1.18	0.043	1.18	0.043		

 $^{^1\,}Accura\,Xtreme\,White\,200\,was\,also\,previously\,marketed\,under\,the\,Visijet^{\circ}\,SL\,Impact\,name\,for\,the\,Projet\,6000\,and\,7000\,printers$





www.3dsystems.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2018 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, the 3D Systems logo, ProX, Accura, ProJet and VisiJet are registered trademarks of 3D Systems, Inc.